






GRABOPLAST

Grabolett Balett

Technical parameter	Unit	Unit	Result
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	1.7
Wear layer thickness	EN ISO 24340	mm	0.7
Length of rolls	EN ISO 24341	m	20
Width of rolls	EN ISO 24341	m	2
Total weight	EN ISO 23997	kg/m ²	2.1
Residual indentation	EN ISO 24343	max. mm	0.1
Dimensional stability	EN ISO 23999	max.%	±0.2
Reaction to fire	EN 13501-1	class	B _{fl} -S ₁
Curling	EN ISO 23999	max.mm	8
Abrasion group	EN 660-2	group	T
Light fastness	EN ISO 105-B02	grade	> 6
Castor chair	EN 425	-	slight change
Chemical resistance	EN ISO 26987	-	high resistance
Slip resistance	EN 13893	class	DS
Surface treatment			CLP
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
CE MARKING	EN 14041		✓

GRABOPLAST Floor Covering Manufacturers Ltd.
H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
mail@graboplast.hu www.graboplast.hu