







## Grabo Diamond

Technical parameter	Standard	Unit	Result
<b>DESCRIPTION</b>			
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	2,0
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m <sup>2</sup>	2,8
<b>CLASSIFICATION</b>			
European classification	EN 685	class	34/43
<b>PERFORMANCE</b>			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0,1
	EN ISO 24343	measured mm	0,01
Dimensional stability	EN ISO 23999	max.%	0,2
Fire resistance	EN 13501-1	class	Bfl-s1
Slip resistance	DIN 51130		R10
Electrical resistance	EN 1815	kV	< 2
Chemical resistance	EN ISO 26987		✓
Bacterial resistance	EN ISO846:1999		✓
Light fastness	EN 20105 B02	grade	6
Castor chair resistance	EN ISO 4918		✓
Surface treatment			X-PUR
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes		 	Phthalate-, solvent and heavy metal free product
VOC			✓
Seaming method			heat or cold weld
Warranty		year	10
CE MARKING	EN 14041		✓