





ACOUSTIC 43

Technical datasheet

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	3,2
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	25
Total weight	EN ISO 23997	kg/m ²	2,7
CLASSIFICATION			
European classification	EN 685	class	34/42
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0,2
Dimensional stability	EN ISO 23999	max. %	0,2
Fire resistance	EN 13501-1	class	Bfl-s1
	BS 476		Class 1
	Gost 30402-94		G1
Impact sound reduction	EN ISO 717-2	DLw (dB)	19
Slip resistance	DIN 51130		R10
Electrical resistance	EN 1815	kV	< 2
	EN 1081	Ω	≤ 10 ⁹
Chemical resistance	ASTM F 925		✓
Bacterial resistance	EN ISO846:1999		✓
Light fastness	EN 20105 B02	grade	6
Castor chair resistance	EN 425		✓
Surface treatment			X-PUR
Anti-bacterial and fungicid treatment			graboSAN
Environmental attributes	 		Phthalate, Solvent and Heavy metal free product
Seaming method			heat or cold weld
Warranty		year	10
CE MARKING	EN 14041		✓