



# Color 20

Technical datasheet

Technical parameter	Standard	Unit	Result
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	2,0
Wear layer thickness	EN ISO 24340	mm	0,9
Length of rolls	EN ISO 24341	m	21
Width of rolls	EN ISO 24341	m	2
Total weight	EN ISO 23997	kg/m <sup>2</sup>	2,6
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	±0,2
Light fastness	EN ISO 105-B02	grade	6
Abrasion group	EN 660-2	group	T
Reaction to fire	EN 13501-1	class	Cfl-s1
Slip resistance	EN 13893	class	DS
Chemical resistance	EN ISO 26987	-	high resistance
Castor chair resistance	ISO 4918 / EN 425		slight change
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Seaming method			Heat welding
Warranty		years	13
CE MARKING	EN 14041		✓