



# JSC E

Technical datasheet

Technical parameter	Standard	Unit	Result
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	2,5
Wear layer thickness	EN ISO 24340	mm	0,5
Length of rolls	EN ISO 24341	m	21
Width of rolls	EN ISO 24341	m	2
Total weight	EN ISO 23997	kg/m <sup>2</sup>	2,3
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max. %	±0,2
Light fastness	EN ISO 105-B02	grade	6
Abrasion group	EN 660-2	group	T
Reaction to fire	EN 13501-1	class	Cfl-s1
Slip resistance	EN 13893	class	DS
Chemical resistance	EN ISO 26987	-	high resistance
Castor chair resistance	ISO 4918 / EN 425		slight change
Antibacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Seaming method			Heat welding
Warranty		years	7
CE MARKING	EN 14041		✓