

GRABOREX 40

Technical datasheet

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			acoustic dampproof underlay
Thickness	EN ISO 24346	mm	4,0
Width of roll	EN ISO 24341	cm	145
Length of roll	EN ISO 24341	lm	25
Weight	EN ISO 23997	kg/m ²	1,8
CLASSIFICATION			
Dimensional stability	EN ISO 23999	max. %	0,2
PERFORMANCE			
Fire resistance	EN 13501-1	class	Bfl-s1
Content of PCP	EN 12673		does not contain
Formaldehyde emission	ENV 717-1		E1 (no emission)
Warranty		year	5
GRABOPLAST Floor Covering Manufacturers Ltd. H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100 mail@graboplast.hu www.graboplast.hu			