

# PROTECTSPORT ARENA

Technical datasheet

Technical parameter	Standard	Unit	Result
<b>DESCRIPTION</b>			
Construction			protecting covering
Thickness	EN ISO 24346	mm	1,6
Width of roll	EN ISO 24341	cm	200
Length of roll	EN ISO 24341	lm	25
Hardness Shore A	ISO 868		92
Weight	EN ISO 23997	kg/m <sup>2</sup>	2,2
<b>CLASSIFICATION</b>			
Dimensional stability	EN ISO 23999	max. %	0,1
Residual indentation	EN ISO 24343	max. mm	0,05
<b>PERFORMANCE</b>			
Fire resistance	EN 13501-1	class	Bfl-s1
Tensile strength	ISO 1421B	N/5cm	450/400
Elongation at break	ISO 1421B	%	160/150
Tear strength	ISO 4674A2	N	15/20
Abrasion resistance	ISO 9352	TaberH18 1000C max. mg	200
Light fastness	ISO 105-B02	48 hours	min.6
Content of PCP	EN 12673		does not contain
Formaldehyde emission	ENV 717-1		E1 (no emission)
Warranty	At least for min 5 times/year	year	3
	Less then 5 times/year	year	4
<b>GRABOPLAST Floor Covering Manufacturers Ltd.</b> H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100 mail@graboplast.hu www.graboplast.hu			