

GRABO HABITAT SOUND 20

Technical datasheet

| Technical parameter | Standard | Unit | Result |
|-------------------------|-----------------------------|-------------------|-------------------|
| DESCRIPTION | | | |
| Construction | | | heterogeneous |
| Total thickness | EN ISO 24346 | mm | 3,5 |
| Wear layer thickness | EN ISO 24340 | mm | 0,3 |
| Width of roll | EN ISO 24341 | m | 2 |
| Length of roll | EN ISO 24341 | lm | 20 |
| Total weight | EN ISO 23997 | kg/m ² | 2,2 |
| CLASSIFICATION | | | |
| European classification | EN 651 | class | 23/31 |
| PERFORMANCE | | | |
| Abrasion group | a priori EN 651 | class | T |
| Residual indentation | EN ISO 24343 | max. mm | 0,2 |
| Dimensional stability | EN ISO 23999 | max.% | 0,2 |
| Impact sound reduction | EN ISO 717-2 | DLw (dB) | 20 |
| Slip resistance | EN 13893 | class | DS |
| Chemical resistance | EN ISO 26987 | | ✓ |
| Light fastness | EN ISO 105-B02 3. method | grade | 6 |
| Castor chair resistance | EN 425 | | ✓ |
| Seaming method | | | heat or cold weld |
| Warranty | | year | 5 |
| CE MARKING | EN 14041 | | ✓ |