




STRONG

Technical datasheet

| Technical parameter | Standard | Unit | Result |
|---------------------------------------|---|-------------------|---|
| DESCRIPTION | | | |
| Construction | | | compact heterogeneous |
| Total thickness | EN ISO 24346 | mm | 2,0 |
| Wear layer thickness | EN ISO 24340 | mm | 0,7 |
| Width of roll | EN ISO 24341 | m | 2 |
| Length of roll | EN ISO 24341 | lm | 20 |
| Total weight | EN ISO 23997 | kg/m ² | 2,8 |
| CLASSIFICATION | | | |
| European classification | EN 685 | class | 34/43 |
| PERFORMANCE | | | |
| Abrasion group | MSZ EN 660-1 | class | T |
| Residual indentation | EN ISO 24343 | max. mm | 0,1 |
| Dimensional stability | EN ISO 23999 | max.% | 0,2 |
| Fire resistance | EN 13501-1 | class | Bfl-s1 |
| Slip resistance | DIN 51130 | | R11 |
| | RRL Pendulum Test | | >55 (wet test) |
| Chemical resistance | EN ISO 26987 | | ✓ |
| Light fastness | EN 20105 B02 | grade | 6 |
| Castor chair resistance | EN ISO 4918 | | ✓ |
| Surface treatment |  | | Easy Care PUR |
| Anti-bacterial and fungicid treatment |  | | graboSAN |
| Enviromental attributes |  | | Phthalate, Solvent and Heavy metal free product |
| Seaming method | | | heat or cold weld |
| Warranty | | year | 10 |
| CE MARKING | EN 14041 | | ✓ |