

# Conducto S

Technical datasheet

Technical parameter	Standard	Unit	Result
<b>DESCRIPTION</b>			
Construction	EN ISO 10581		Homogeneous flooring, Type I.
Total thickness	EN ISO 24346	mm	2.0
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Wear layer thickness	EN ISO 24340	mm	2.0
Total weight	EN ISO 23997	kg/m <sup>2</sup>	2.8
<b>CLASSIFICATION</b>			
Binder content	EN ISO 10581	class	Type I.
European classification	ISO 10874	class	34 / 43
Residual indentation	EN ISO 24343-1	max. mm	0.1
Dimensional stability	EN ISO 23999	max.%	0.4
Curling	EN ISO 23999	max. mm	8
<b>PERFORMANCE</b>			
Fire resistance	EN 13501-1	class	Bfl-s1
Slip resistance	DIN 51130		R9
	EN 13893		DS
Light fastness	EN ISO 105-B02	grade	6
Electrical resistance	EN 1815	kV	< 2 / Antistatic
	EN 1081	Ω	$R \leq 1 \times 10^6$
Chemical resistance	EN ISO 26987		✓
Hygiene			Bacterial resistant
Castor chair resistance	ISO 4918		✓
Surface treatment			iGUARD PUR Surface
Environmental attributes			Phthalate-, solvent and heavy metal free
Seaming method			heat or cold weld
Content of PCP	EN 12673		Does not contain
Formaldehyde emission	ENV 717-1		E1 (no emission)
<b>GRABOPLAST Floor Covering Manufacturers Ltd.</b> H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100 mail@graboplast.hu www.graboplast.hu			