

# TERRANA 16

Technical datasheet

Technical parameter	Standard	Unit	Result
<b>DESCRIPTION</b>			
Construction			heterogeneous
Total thickness	EN ISO 24346	mm	1,4
Wear layer thickness	EN ISO 24340	mm	0,15
Width of roll	EN ISO 24341	m	2 / 3 / 4
Length of roll	EN ISO 24341	lm	28-33
Total weight	EN ISO 23997	kg/m <sup>2</sup>	1,25
<b>CLASSIFICATION</b>			
European classification	EN 653	class	21
<b>PERFORMANCE</b>			
Abrasion group	a priori EN 651	class	T
Residual indentation	EN ISO 24343	max. mm	0,35
Dimensional stability	EN ISO 23999	max.%	0,2
Impact sound reduction	EN ISO 717-2	DLw (dB)	13
Slip resistance	EN 13893	class	DS
Chemical resistance	EN ISO 26987		✓
Light fastness	EN ISO 105-B02 3. method	grade	6
Castor chair resistance	EN 425		✓
Seaming method			heat or cold weld
Warranty		year	3
CE MARKING	EN 14041		✓